

Technical data

160g/m² - 2 sides coated

GRIP
SHEET®

TEST	UNIT	NORM	VALUE	SPECIFICATIONS
■ Weight final product	g/m ²	NF EN ISO 536, 1996	188	183 - 192
■ Thickness	µm	NF EN ISO 534, 2005	326	295 - 356
BREAKING STRENGTH IN TENSION				
■ Resistance	kN/m	NF EN ISO 1924.2, 1995	SM	9,02
			ST	3,71
■ Rupture length	meters		SM	5181
			ST	2131
■ Elongation	%		SM	2,1
			ST	3,3
■ Burst Index	kPa	NF EN ISO 2758, 2004		333
■ Friction coefficient	°	NF Q 03-083,1993	SM	51,1
■ air porosity	cm ³ /m ² .Pas	NF ISO 5636.3, 1992		14
■ toxicity				None
■ Skin irritation				None
■ Reuse		NF EN 13429		Yes
■ Recyclability				Yes



- Pallet quantity = 3,500 sheets
- % of tolerance : 2%
- Warehousing conditions: Insensitive to heat/cold